

STOBITAN[®] SC

Porous textured surface



 **STOCKMEIER**
URETHANES

Support Porous macadam / concrete.

	Product	Quantity kg/m²
Primer	Stobielast[®] S 100.00 or Stobielast[®] S 080.00	0.15 kg
Base layer 11- 12 mm	Stobielast[®] S 135.00 (1 component)	1.60 kg
	SBR rubber 1- 4 mm	7.80 kg
Surface 1-2 mm	Stobielast[®] S 125.[..] (1 component)	1.20 kg
	EPDM rubber 0.5 – 1.5 mm	0.80 kg

Stockmeier Uréthanes France SAS
8, Rue de l'Industrie
Z.I. Est
68700 Cernay
FRANCE
T +33 (0)3 89 75 70 70
F +33 (0)3 89 75 70 81
snad@snad.fr
urethanes.fr@stockmeier.com
www.stockmeier-urethanes.com

[..] = The last two digits of the product code mark the color of the product

Total thickness around 13 mm

Applications Running tracks
Multipurpose systems

Test Reports & Certificates IAAF Test report and certificate # S 05-0057
DIN18035 Part 6 : Environmental compatibility
EN 14877: 2013 : European Sport Specifications
EN 13501/ISO 11925-2
ITB (Poland)

Edition August 2014